



Intertape PG777 Technical Datasheet



Product Description

PRODUCT APPLICATION Paint masking, either OEM or repair. Allows clean removal from aluminum, primed aluminum, and painted aluminum surfaces even when cycled three or more times.

GOVERNMENT COMPLIANCE BAC 5034-4

STORAGE RECOMMENDATION Store new stock behind current stock. Store in a clean, dry place. Temperature of 70°F (21°C) +/- 6°F, and 40% to 50% relative humidity are recommended.

SHELF LIFE When stored under recommended conditions, converted rolls have an expected shelf life of up to one (1) year from the date of shipment. Jumbo rolls have the same expected shelf life, but it is recommended that they are converted within six (6) months of date of shipment.

NOMINAL VALUES The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing – Smooth Crepe Paper

Adhesive – Natural Rubber / Resin

Adhesion to Steel (oz/in of width) – 30 (8.2 N/25mm)

Tensile Strength (lbs/in of width) – 30 (131.3 N/25mm)

Total Thickness (mils) – 7.7 (0.196mm)

Quick Stick (oz/in of width – 17 (4.7 N/25mm)

Commodity Code: 3919100000

SKU: FA-PG777

Product Description

A pressure-sensitive masking tape designed primarily for the aircraft industry where resistance to strong solvent / high solids polyurethane-based paints is a necessity. Adhesive is specially formulated to provide excellent adhesion to, and transfer free removal from, a variety of prepared aluminum surfaces. Product is able to support large kraft aprons. It will perform in cycle-bake applications of 140°F for 4-6 hours for up to three cycles. Conformable, extra-strong smooth crepe paper backing provides clean paint break lines and strength for pulling long paint lines with clean, tear-free removal. The release coating is also designed to resist paint flaking upon removal. Not recommended for outdoor use.

PRODUCT APPLICATION Paint masking, either OEM or repair. Allows clean removal from aluminum, primed aluminum, and painted aluminum surfaces even when cycled three or more times.

GOVERNMENT COMPLIANCE BAC 5034-4

STORAGE RECOMMENDATION Store new stock behind current stock. Store in a clean, dry place. Temperature of 70°F (21°C) +/-

6°F, and 40% to 50% relative humidity are recommended.

SHELF LIFE When stored under recommended conditions, converted rolls have an expected shelf life of up to one (1) year from the date of shipment. Jumbo rolls have the same expected shelf life, but it is recommended that they are converted within six (6) months of date of shipment. **NOMINAL VALUES** The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing – Smooth Crepe Paper

Adhesive – Natural Rubber / Resin

Adhesion to Steel (oz/in of width) – 30 (8.2 N/25mm)

Tensile Strength (lbs/in of width) – 30 (131.3 N/25mm)

Total Thickness (mils) – 7.7 (0.196mm)

Quick Stick (oz/in of width) – 17 (4.7 N/25mm)

Frasers Aerospace, 1 St James Road, Brentwood, Essex, CM14 4LH

Tel: +4420 8597 8781 Email: contact@frasersaerospace.com Web: www.frasersaerospace.com